

ROOFING APPLICATIONS



Roofing Applications Specifications Sheet

PROPERTIES	ASTM Test Method	PMAB-28 Resid	RS-110	PMA-86
ORIGINAL BINDER		SPEC	SPEC	SPEC
Viscosity at 275 °F CST	D-2170			
Minimum		165	130	
Maximum		190	145	
Rotational Viscosity at 400 °F, cPs	D-4402			
Minimum				155
Maximum				250
Penetration at 77 °F	D-5			
Minimum			120	18
Maximum			150	29
Flash COC °F	D-92			
Minimum		500	510	210
Softening Point, °F	D-36			
Minimum			95	215
Maximum				235

T: 661-327-4257

F: 661-327-3236

3500 Shell Street, Bakersfield, CA 93308

